

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-157052

(43)Date of publication of application : 17.06.1997

(51)Int.Cl.

C04B 35/83

C01B 31/02

C04B 35/80

C04B 38/06

H01M 4/88

H01M 4/96

(21)Application number : 07-345261

(71)Applicant : TORAY IND INC

(22)Date of filing : 06.12.1995

(72)Inventor : INOUE MIKIO

(54) POROUS CARBON SHEET AND ITS PRODUCTION

(57)Abstract:

PROBLEM TO BE SOLVED: To produce a porous carbon sheet having increased gas permeability in the thickness direction while keeping the mechanical strength relatively high and the specific resistance in the thickness direction relatively high.

SOLUTION: Short carbon fibers dispersed in random directions in a practically two-dimensional plane are bonded to one another with carbon to obtain the objective porous carbon sheet having ≥ 14.7 MPa bending strength, ≥ 0.49 MPa compressive strength in the thickness direction, ≤ 11.8 MPa modulus of compressive elasticity in the thickness direction, ≤ 0.010 m specific resistance in the thickness direction and $\geq 3,000$ ml.mm/cm²/hr/mmAq gas permeability in the thickness direction in air.

LEGAL STATUS

[Date of request for examination]

24.10.2001

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office